

Product Specification: Northern Quarries 14/10mm Class GP Aggregate

PRODUCT CODE: 0605

SOURCE ROCK TYPE: Basalt

CUSTOMER: Standard Product

REFERENCE: VicRoads Standard Specifications for Road works and Bridgeworks, Section 801
AS2758.1 – Aggregates and Rock for Engineering Purposes, Concrete Aggregates


Relevant Tests Carried Out On Source Rock				
Test	Method	Frequency	Requirements	Reference
Los Angeles (LA) Value	AS1141.23	VicRoads Issue	≤30	AS2758.1.9.3.3
Preparation of Reference Specimens	AS1141.30 Appendix A	VicRoads Issue	See below for sound and marginal classifications	VicRoads 801.04
Accelerated Soundness by Reflux	AS1141.29	VicRoads Issue	Sound ≥94% Marginal 90-93%	VicRoads 801.031 & 801.032
Secondary Mineral Content	AS1141.26	VicRoads Issue	Sound ≤25% Marginal 26-30%	VicRoads 801.031 & 801.032

Tests Carried Out For Product Quality Control Purposes

Sampling Method: AS1141.3.1

Test	Method	Frequency	Requirements	Reference
Unit Mass Density	AS1141.4	1 per 3 Years	N/A – For reference purposes only	N/A
Particle Density (Coarse Agg)	AS1141.6	1 per 3 Years	≥2.1t/m ³ , <3.2t/m ³	AS2758.1.7.1
Particle Shape by Proportional Calliper	AS1141.14	1 per year	≤10% using 3:1 ratio	AS2758.1.8.3
Flakiness Index (FI)	AS1141.15	1 per 9,600t	≤35%	AS2758.1.8.3
Unsound stone count by visual assessment	AS1141.30 / RC372.01	1 per 4,800t	Unsound ≤5% Marginal + Unsound ≤10%	AS2758.1.9.3.4
Particle size distribution (Grading)	AS1141.11 (washed)	1 per 2,400t	See table below	AS2758.1.8.1.3

Sieve Size AS (mm)	Limits of Grading (% Passing)	Limits of Deviation %	Target Grading (% Passing)
19.0	100	-	100
13.2	85 – 100	±10	92
9.50	20 – 60	±15	40
6.70	5 – 15	±15	10
4.75	0 – 5	±5	2
2.36	0 - 10	-	1
0.075	0 – 2	-	1



Date issued: 28 Aug 2006
Issue number: 2
Authorised by: Tom Kerr
Date printed: 7 Aug 2009

Previous issue date: 9 May 2002

Date of first issue: 9 May 2002
Max review interval: 5 years
Manual index location: 19.i
Form: 2005.06